

# HS - 55AH

		SI	CGS
残留磁束密度 Residual Induction	$B_r$	1.48 ~ 1.52 T	14.8 ~ 15.2 kG
保磁力 Coercive Force	$bH_c$	994 ~ 1178 kA/m	12.5 ~ 14.8 kOe
	$iH_c$	1034 min kA/m	13.0 min kOe
最大エネルギー - 積 Maximum Energy Product	$(BH)_{max.}$	421 ~ 446 kJ/m <sup>3</sup>	53 ~ 56 MGOe

